

Aladdin warrants, that at the time of the quality release or subsequent retest date this product conformed to the information contained in this publication. The current Specification sheet may be available at Aladdin-e.com. For further inquiries, please contact Technical Service. Purchaser must determine the suitability of the product for its particular use. See reverse side of invoice or packing slip for additional terms and conditions of sale.

## **Specification Sheet**

Product Name: Poly(1,4-phenylene sulfide)
Specifications & Purity: 40% glass fiber reinforced

SKU# **P477572** 

Parameter Limit Values

Appearance(P477572) White to Off-White Solid

Tensile strength 130-150 (MPa)
Melting Temperature 270-290 (°C)
Dielectric Strength 15-17 (KV/mm)

Infrared spectrum Conforms to Structure

Tensile strain at break 1.5-1.7 (%)

Aladdin warrants, that at the time of the quality release or subsequent retest date this product conformed to the information contained in this publication. The current Specification sheet may be available at Aladdin-e.com. For further inquiries, please contact Technical Service. Purchaser must determine the suitability of the product for its particular use. See reverse side of invoice or packing slip for additional terms and conditions of sale.

Phone: +86 400 620 6333 Email: Sale@aladdin-e.com Web: https://www.aladdin-e.com