

Aladdin warrants, that at the time of the quality release or subsequent retest date this product conformed to the information contained in this publication. The current Specification sheet may be available at Aladdin-e.com. For further inquiries, please contact Technical Service. Purchaser must determine the suitability of the product for its particular use. See reverse side of invoice or packing slip for additional terms and conditions of sale.

Specification Sheet

Poly(L-lactide-co-glycolide)
ester terminated, Lactide: Glycolide 82:18
P299054

Parameter	Limit Values
Heavy metals	0-10 (ppm)
Tin(Sn)	0-60 (ppm)
Residual solvents(GLC-HS)(toluene)	0-890 (ppm)
Water by Karl Fischer	0-0.5 (%)
Sulfate Ash	0-0.1 (%)
Inherent Viscosity(0.1% in CHCl3,25°C)	1.7-2.6 (DL/G)
Glycolide(Quantitative NMR)	15-21 (Mole%)
L-Lactide(GC)	0-1 (wt%)
L-Lactide(Quantitative NMR)	78-85 (Mole%)
Glycolide(GC)	0-1 (wt%)
Appearance (P299054)	White to Off-White Powder or Granules
Odor (almost odorless)	pass
Proton NMR spectrum	Conforms to Structure

Aladdin warrants, that at the time of the quality release or subsequent retest date this product conformed to the information contained in this publication. The current Specification sheet may be available at Aladdin-e.com. For further inquiries, please contact Technical Service. Purchaser must determine the suitability of the product for its particular use. See reverse side of invoice or packing slip for additional terms and conditions of sale.