

Aladdin warrants, that at the time of the quality release or subsequent retest date this product conformed to the information contained in this publication. The current Specification sheet may be available at Aladdin-e.com. For further inquiries, please contact Technical Service. Purchaser must determine the suitability of the product for its particular use. See reverse side of invoice or packing slip for additional terms and conditions of sale.

Specification Sheet

Product Name: **DOWSIL™ 736 Heat Resistant Sealant**
 Specifications & Purity:
 SKU # **D487429**

Parameter	Limit Values
Non-Volatile Content (5g/70C/24h/Al Cup)	92-100 (%)
Durometer(Shore A)	≥20
Tensile Strength (psi)	≥220
Elongation (3d/RT)	≥350 (%)
180 degree Peel Strength(Low Carbon Panel/SS Strips - 3d/RT)(lb/in)	≥14
180 degree Peel Strength(Aluminum Panel/SS Strips - 3d/RT)(lb/in)	≥14
Tack free time	0-25 (Min)
Specific Gravity(RT/50% RH)	1.01-1.07
Extrusion rate	220-460 (g/min)

Aladdin warrants, that at the time of the quality release or subsequent retest date this product conformed to the information contained in this publication. The current Specification sheet may be available at Aladdin-e.com. For further inquiries, please contact Technical Service. Purchaser must determine the suitability of the product for its particular use. See reverse side of invoice or packing slip for additional terms and conditions of sale.